



# Certified Reference Material

## Certificate of Analysis



### Manufacturers Details

**KLEN International (74) Pty Ltd**  
 36 Hemisphere Street  
 Neerabup, Western Australia, 6031

PO Box 529  
 Wanneroo WA 6946

### Concentration of Certified Analyte/s

<b>Au</b>	<b>0.154 g/t (ppm)</b>
<b>CRM Type Oxide</b>	

### Identifiers

Batch number : 74217  
 Stock Code Unit (2kg jar) : 21001021  
 Stock Code Unit (30g sachet) : 21001023  
 Stock Code Unit (50g sachet) : 21001025  
 Stock Code Unit (150g sachet) : 21001027  
 Date of Manufacture : April 2017  
 Certificate Period of Validity : 72 months

NB: For ease of documentation, only the larger pack size is referenced throughout the CoA. However, product making up all jars and sachets originate from the same batch number.

### Intended Use

This product is for use as a reference material for monitoring and testing the accuracy of laboratory analysis of minerals and ores.

### Analyte Data Table

Analyte	Certified Value g/t	Measurement Uncertainty g/t	Number of Laboratories
Au	0.154	0.008	23



# Certified Reference Material

## Certificate of Analysis



### Notes related to information contained in the Analyte Data Table

**Certified Value** – (CV) is the mean of means from accepted values of all participating round robin laboratories.

**Measurement Uncertainty** - (MU) is a statistical measure of the variability associated with multiple procedures used, between unit and within unit inhomogeneity, and changes during storage and transport (unless the certification notes differences in method). MU *does not take into account* individual laboratory bias and also excludes results from laboratories who were considered to be outliers.

The MU reported for this reference material does not take into account the effects due to transport. Consequently adequate mixing in the container before use is recommended.

The long term stability of this product under recommended storage conditions is monitored.

**Number of Laboratories** – is the number of participating round robin laboratories who returned data that was included in the calculation of the CV and all subsequent statistics.

### Homogeneity Testing

Homogeneity testing forms the initial acceptance for the suitability of each batch. The testing program has been designed by an independent statistician and is followed as part of KLEN's internal quality control procedures. The analytical data returned from homogeneity testing is statistically analysed to confirm suitability for advancement of the batch to the round robin stage of testing at multiple laboratories.

### Homogeneity Test Results

Analyte/s of interest	Au
Number of samples tested	30
Duplicate assays performed on each sample	Yes
Number of outlying results rejected	Nil
Mean g/t (ppm)	0.166
Relative standard deviation %	3.5%



# Certified Reference Material

## Certificate of Analysis



### Additional Statistical Data

Standard Deviation g/t	Relative Standard Deviation %	95% Measurement Confidence Interval g/t
0.009	6.2	$0.154 \pm 2 * 0.008$

### Notes related to information contained in the Additional Statistical Data Table

**Standard Deviation** – the Standard Deviation is the standard deviation of the laboratory means provided by the participating round robin laboratories, excluding any outlying results.

**Relative Standard Deviation** – the Relative Standard Deviation is the Standard Deviation value divided by the CV

**95% Measurement Confidence Interval** - is the  $CV \pm 2 * MU$  based on the accepted data provided by the participating round robin laboratories. An unbiased laboratory, using the same analytical method and instrumentation, should be able to achieve a result within the quoted interval 95% of the time. It is *not* an indication of the control limits or variability that any given laboratory may choose to impose, or achieve, for their own testing and unique situation. The 95% Confidence Interval excludes any outlying laboratory results.

### Compliance with ISO Standards & Guides

KLEN manufacture all CRM's in accordance with the following ISO Standards & Guides;

- ISO 17034:2016 General requirements for the competence of reference material producers
- ISO Guide 31-2015 Reference materials - Contents of certificates labels and accompanying documentation
- ISO Guide 35-2006 Reference materials - General and statistical principles for certification

### Round Robin Laboratories

Samples of batch 74217 were taken in accordance with the sampling plan and placed in heat sealed foil sachets. Each sachet contained sufficient sample to allow duplicate assays to be performed. The samples were distributed to 30 participating laboratories for round robin analysis, of which 25 returned results within the specified time period. After analysis of the results, 2 laboratories were removed as statistical outliers. Laboratories were requested to perform fire assay analysis using 50 gram sample weights. Final analysis was achieved via each laboratories routine instrument finish.





# Certified Reference Material

## Certificate of Analysis



### Participating Laboratories

Company	Location		Country
Independent Assay Labs	Perth	WA	Australia
Newmont Mining - Phoenix Mine	Battle Mountain	Nevada	USA
PT Intertek Utama Services	Pekayon, Pasar Rebo	Jakarta	Indonesia
Swastika Lab LTD.	Swastika	Ontario	Canada
On Site Laboratory Services	Bendigo	Victoria	Australia
Inspectorate de Mexico SA de CV	Hermosillo	Sonora	Mexico
Intertek Minerals	Maddington	WA	Australia
Activation Labs	Thunder Bay	Ontario	Canada
SGS	Perth	WA	Australia
MS Analytical	Langley	BC	Canada
Activation Labs	Kamloops	BC	Canada
Activation Labs		Coquimbo	Chile
Inspectorate America Corporation	Sparks	NV	USA
Activation Labs	Ancaster	Ontario	Canada
American Assay Laboratories	Sparks	Nevada	USA
Semafo	Ouagadougou		Burkina Faso
ALS Chemex (Orange)	Orange	NSW	Australia
ALS GLOBAL (Vancouver)	North Vancouver	B.C.	Canada
MinAnalytical	Perth	WA	Australia
SGS		Tarkwa	Ghana
Suriname Gold/Newmont		Paramaribo	Suriname
Intertek Minerals	Townsville	Queensland	Australia
Intertek Minerals		Accra	Ghana
Newmont Mining - Twin Creeks Mine	Golconda	Nevada	USA
ALS Chemex (Malaga)	Malaga	WA	Australia
Kappes, Cassiday & Associates	Reno	Nevada	USA
SGS		Ahafo	Ghana
ALS Chemex (Townsville)	Townsville	QLD	Australia
Intertek Minerals	Adelaide	SA	Australia
ALS Minerals	Reno	Nevada	USA



# Certified Reference Material

## Certificate of Analysis



### Minimum Sample Size

The majority of laboratories utilised 50 gram sample weights for Gold analyses as requested. Non-outlying data from laboratories that used 30gram sample weights has been included in the statistical analysis.

While lower sample weights may be employed, the certified value and its associated uncertainty are not guaranteed where less than the following sample weights are used:

- Gold (non-gravimetric) 30 grams

### General Product Description

KLEN CRM's are manufactured from blended raw materials to provide a suitable substrate for the analytes of interest. Substrates will vary to provide a background matrix as may be required or suited for particular applications. Starting materials are oven dried for a minimum of 24 hours to remove any moisture. Dried material is then milled and screened to ensure no oversize particles or product agglomerations are present. Required analytes are treated in a similar fashion to ensure they match the particle size of the substrate and can be uniformly distributed throughout the batch.

### Instructions for Storage Handling and Use

KLEN CRM's are provided in hermetically sealed jars or sachets. Unopened containers should be stored in a cool dry place. Jar contents should be mixed thoroughly on opening before use. Once jars are opened, the contents can be protected by resealing the inner packaging using the bag clip provided, prior to securely replacing the lid on the container. After opening, jars should be stored in a cool dry place. Sachets are designed for immediate use once opened.

### Safety Data Sheet (SDS)

The SDS for the product is available on line from the KLEN website at [www.klen.com.au](http://www.klen.com.au)  
Direct access is provided via the QR code below.



[http://www.klen.com.au/CRM/Certificates\\_of\\_Analysis/SDS\\_21001021\\_Oxide.pdf](http://www.klen.com.au/CRM/Certificates_of_Analysis/SDS_21001021_Oxide.pdf)

*Together we can achieve the Extraordinary*

**KLEN INTERNATIONAL (74) Pty Ltd**

PO Box 529, Wanneroo WA 6946; 36 Hemisphere Street, Neerabup Western Australia 6031  
T +61 8 9306 8900 F +61 8 9306 8922 E [info@klen.com.au](mailto:info@klen.com.au) W [www.klen.com.au](http://www.klen.com.au)  
ABN 25 008 776 681

Page 5 of 8





# Certified Reference Material Certificate of Analysis



## Product Certification

Batch 74217 was packed into 500 jars and samples were taken in accordance with a random sampling plan as developed by external statisticians. Four samples were then sent to each of 30 participating laboratories for analysis in duplicate. Samples were analysed using fire assay with the instrument finish being left to each laboratory.

## Use of Certified Data

The certified value/s provided within this document are entirely reliant on the data returned from the participating testing laboratories. Analysis of the data is conducted by a third party statistical service who acts independent of KLEN International (74) P/L. Determining the suitability of this product shall be the sole responsibility of the user and application of information contained within this document is at the sole discretion of the user. Through receipt and application of the information contained herein, the user indemnifies and releases both KLEN International (74) P/L and the Centre of Applied Statistics, University of Western Australia from any claim arising from use, application, and any subsequent actions related to the certified data. No warranty either expressed or implied other than the fitness for sale to the above specification is made.

## Independent Statistical Analysis

All raw and unaltered data returned from participating round robin laboratories is made available simultaneously to KLEN International (74) P/L and an independent statistical service. Once data returns are complete, analysis is conducted by the independent statistical service and all critical statistical figures are finalised. Statistical data from the final independent analysis are utilised in this report.

## Statistical & Administrative Certifications

We the undersigned verify that the information contained within this certificate is a true and accurate representation of the product described herein.

Dr Alethea Rea BSc (Hons) PhD  
Research Fellow, Centre of Applied Statistics  
University of Western Australia

Mr B. van Blommestein MRACI C CHEM(A)  
Chemist  
KLEN International (74) Pty Ltd





# Certified Reference Material

## Certificate of Analysis



### Revision Information

ver 1.1	Revision Date :	July 2018
	Revision Summary:	Replacement of standard error with measurement uncertainty in analyte data table. Various amendments and inclusions in order to comply with requirements of ISO 17034 accreditation.
ver 2.0	Revision Date:	April 2020
	Revision Summary:	Extension of Period of Validity of Certificate of Analysis on the basis of stability testing undertaken in accordance with the requirements of ISO 17034.

### **SUPPLEMENTARY INFORMATION**


NB: The test results that follow are outside the scope of accreditation for ISO 17034, and are included for information purposes only.

### Particle Size

Particle size analysis was performed on 5 samples of SKU 21001021, batch number 74217, using a Shimadzu SALD-2300 laser diffraction particle sizer with SALD-DS5 dry injection, sample introduction unit.

The averaged results for 5 samples provided the following data;

Median particle diameter (micron)	18
Modal particle diameter (micron)	24
Mean particle size (micron)	14
Standard deviation of Mean (%)	0.422
Particle size for cumulative 90% of product (micron)	44



*Together we can achieve the Extraordinary*

**KLEN INTERNATIONAL (74) Pty Ltd**

PO Box 529, Wanneroo WA 6946; 36 Hemisphere Street, Neerabup Western Australia 6031  
 T +61 8 9306 8900 F +61 8 9306 8922 E info@klen.com.au W www.klen.com.au  
 ABN 25 008 776 681





# Certified Reference Material



## Certificate of Analysis

### Product Description

SKU 21001021 batch number 74217, is a dry and uniform powder with a light grey colour. The chemical composition was determined by XRF analysis as follows;

Content	%
SiO2	63.0
Al2O3	17.3
CaO	3.48
Fe	2.85
K2O	4.28
MgO	1.79
Na2O	5.00
P	0.057
S	0.03
TiO2	0.64
Cl	0.0075
Moist	0.23
LOI	0.26

### Typical Geological Analysis

X-Ray diffraction analysis provided the following crystalline and amorphous content information.

Phase	Formula	wt %
Amorphous content		<15
Augite	(Ca,Na)(Mg,Fe,Al,Ti)(Si,Al)2O6	30 - 40
Fayalite	Fe2SiO4	<5
Ilmenite	FeTiO3	<5
Magnetite	Fe3O4	<5
Pyrite	FeS2	<1
Quartz	SiO2	<1
Sodium Calcium Plagioclase	(Na,Ca)(Al,Si)2Si2O8	40 - 50

*Together we can achieve the Extraordinary*

**KLEN INTERNATIONAL (74) Pty Ltd**

PO Box 529, Wanneroo WA 6946; 36 Hemisphere Street, Neerabup Western Australia 6031

T +61 8 9306 8900 F +61 8 9306 8922 E info@klen.com.au W www.klen.com.au

ABN 25 008 776 681

